

GENERAL

LAMICA 21-150 consists of reconstituted calcined muscovite mica pulp. It has uniform appearance, colour and surface. It is free from conductive particles, wrinkles, pin holes cracks and voids. It is flat and even surface so the lamination to other backing material is good.

APPLICATION

LAMICA 21-150 paper is used for manufacturing insulating materials for resin rich application.

PRODUCT CHARACTERISTICS:

Characteristics	Unit	Typical Values	Test Method
Thickness	mm	0.115 ± 0.015	IEC - 60554-2
Total Weight	g/m ²	150 ± 10	IEC - 60554-2
Porosity	s/100 ml	≤ 4000	ISO 3687
Impregnating Time	Sec	≤ 200	IEC - 60371-2
Composition	%	100% Pulp 21	
Width	mm	1040 ± 5	
Length	Mtrs	510 ± 10	
Tensile Strength	N/Cm	≥ 7	IEC - 60371-2

SUPPLY:

Lamica 21-150 should be tightly wound, without folds, on the paper tube of 130 mm ID. Standard length of the roll will be 510 Mtrs and approximate weight of the roll is 77Kgs.

STORAGE & HANDLING INSTRUCTIONS:

LAMICA 21-150 rolls should be covered with polyethene film to prevent ingress of moisture and dust. The rolls should be held in the centre of the core by providing side plates with wooden plugs such that the rolls do not come in contact with the inside surface of the packing boxes. The box containing mica paper roll should be stored in clean and dry place. Blue silica gel packed in polyester cloth / fleece bag will be placed in each box to prevent the ingress of moisture.

SHELF LIFE

There is no recommended shelf life for this item. However, we advise to use the product with in 60 Months.

JOINTS:

Lamica 21-150 produced without joints. Joints if any should be marked with red strips. Wrinkles, hole or cracks should be marked with yellow strips. All such strips should be on right side of the roll and should be clearly visible.

IDENTIFICATION:

Each roll of mica paper should be identified by affixing a sticker containing details such as manufacturing date, roll number, weight, length and gsm.

WORK HYGIENE:

While using LAMICA 21-150 we recommend to follow the necessary Health & Safety Standards.

Rev. 00 / Issue Date: 11.01.2010

LIABILITY: All the above information is based on our own research and experience. We cannot however offer any Guarantee for the information as the manufacturer himself is responsible for any article made with our product. Neither do we accept Liability for any damage which could be caused by the information given hereby

Lakshmanan Isola Pvt. Ltd.

Works: Achalu, Ramanagaram 562 159, Karnataka, India Ph +91 80 2727 1266 / 2727 4996 Fax +91 80 2727 1166
Regd Off: Casa Fina, 5, Primrose Road, Bengaluru 560 025, India Ph +91 80 4112 4001 Fax +91 80 2559 7778